

PLEASE ENTER A.F. Amendment
- 314

LISTING OF CLAIMS:

This listing of claims will replace all prior versions, and listings, of claims in the application.

Please cancel claims 4 and 11 without prejudice or disclaimer of the subject matter set forth therein and amend claims 1 and 7 as follows.

1. (Currently amended) A resin molded product by melt molding of a polyphenylene sulfide resin composition, said polyphenylene sulfide resin composition comprising:

(a) 60 % by weight to 95 % by weight of [[a]] polyphenylene sulfide resin, and

(b) 5 % by weight to 40 % by weight of an olefin resin;

said (a) polyphenylene sulfide resin comprising:

(a-1) 100 parts by weight of a polyphenylene sulfide resin that is not cross-linked by thermal oxidation and having a melt flow rate (315.5°C, 5000g load) of 90 g/10 min to 350 g/10 min measured according to ASTM-D1238, and an amount of extracts by chloroform of 2.2 % by weight to 4.5 % by weight, and

(a-2) 5 parts by weight to 80 parts by weight of a polyphenylene sulfide resin having a melt flow rate (315.5°C, 5000g load) of 50 g/10 min to 800 g/10 min measured according to ASTM-D1238 and an amount of extracts by chloroform of not higher than 1 % by weight and being not cross-linked by thermal oxidation; and

said (b) olefin resin comprising a mixture of:

(b-1) an olefin copolymer prepared by introducing an epoxy group-containing monomer component into an olefin (co)polymer, and